

KEMPLAST

Specification

Property	Unit	Value
Softening point	°C	85~100
Moisture content	%	<0,2
Ash content	%	<0,4
Acid number	mg KOH/g	<0,5
Iodine number	g iodine/100 g	15~60

Product description: Solid substance of dark brown color. Form of production - flakes of up to 4 mm thick. Presence of powder-like particles is permitted.

Production method: Thermal polymerization of heavy pyrolysis resin.

Application: Tire and rubber-processing industries.

Type of packing: 25kg PP bags/40kg PP bags/500kg big bags/1000kg big bags.

Transportation: Clean covered vehicles protected against water penetration, mechanical damages and fouling.

Storage: In covered dry warehouses.